Fiber Cable



Central Loose Tube Armored Cable

Lightem offers a board variety of fiber optic cable for different outdoor condition, such as central loose tube armored cable, duct armored cable, direct buried cable, steel wire armored cable, non metallic outdoor cable, ADSS cable and figure 8 cable. Up to 48 core structure, Central loose tube armored cable is the most popular cable for outdoor installation as of the compact and flexible features. Full range of fiber type ranging from G652D, G657A1/A2, OM1 62.5/125μm, OM2 50/125μm, OM3, OM4 and OM5 are available. Lightem also provides the customization service on the fiber, colours and construction of the cables for catering different cases.

Features

- Fiber count up to 48 core
- Aerial/Duct application
- Waterproof Layer Between the Steel Tape and Cable Core
- PE outer sheath with Corrugated Steel Tape
- Parallel Double Steel Wire as Strengthening Member
- Waterproofing Layer Proving Strong Water-Resistance Performance
- Excellent Anti-crush and Tensile Properties
- Flame retardant or LSZH jacket is available
- Comply to TIA/EIA568C-3 and ISO/IEC 11801
- Economy choice

Fire Performances (Optional)

Flame Retardant	Oxygen Index	Low smoke opacity	Halogen Free
IEC 60332	ISO 4589-3 / ASTM D2863	IEC 61034-2	IEC 60754-1/2

Specifications

General

Flame Rating (For LSZH model only)	LSZH
Fiber Category	Singlemode / Multimode
Temperature Range	
Installation	-5 to +50°C
Operation	-30 to +70°C
Storage	-40 to +70°C
Cable Design - Fiber Count	2-48
Fiber Colouring	Blue, Orange, Green, Brown, Slate, White, Red, Black, Yellow, Violet, Rose,Aqua
Buffer Tube colour	White
Tape	Water-swellable
Tensile Strength Elements and/or Armouring Layer	Smooth steel tape and 2 steel wires
Outer Jacket Material	PE/LSZH
Outer Jacket Colour	Black

Mechanical Characteristics Cable	Unit			
Fiber Count		4,6,8,12	24	48
Outer Diameter (±0.5mm)	mm	9.9	10.6	11.8
Cable weight (±20%)	kg/km	131	148	173
Outer Sheath Thickness	mm		Nominal 2.6	
Max. Tension (Short-term)	N		1500	
Max. Crushing Resistance(Short-term)	N/100mm^2		1000	
Bending Radius(Loading)	D		20	
Bending Radius(Without Loading)	D		10	

Website: www.lightem.com | Email: info@lightem.com | Tel: +852-26875815 | Fax: +852-26875456
© LIGHTEM® Group All rights reserved. Specifications are subject to change without notice

Fiber Core Specifications (Singlemode)

Characteristics		G652D	G657A1	G657A2
Optical Characteristics *				
Attenuation	1310nm	≦0.40 dB/km	≦0.40 dB/km	≦0.40 dB/km
	1383nm	≦0.34 dB/km	≦0.35 dB/km	≦0.35 dB/km
	1460nm	-	≦0.25 dB/km	≦0.25 dB/km
	1490nm	-	-	≦0.23 dB/km
	1550nm	≦0.30 dB/km	≦0.30 dB/km	≦0.30 dB/km
	1625nm	≦0.23 dB/km	≦0.23 dB/km	≦0.23 dB/km
Attenuation vs. Wavelength	1285-1330nm	≦0.03 dB/km	≦0.03 dB/km	≦0.03 dB/km
Max. α difference	1525-1575nm	≦0.02 dB/km	≦0.02 dB/km	≦0.02 dB/km
Dispersion coefficient	1285-1340nm	≧-3.4≦3.4 ps/(nm · km)	≧-3.4≦3.4 ps/(nm · km)	-
	1550nm	≦18 ps/(nm · km)	≦18 ps/(nm · km)	-
	1625nm	≦22 ps/(nm · km)	≦22 ps/(nm · km)	-
Zero dispersion wavelength		1312±12 nm	1300~1324 nm	1300~1324 nm
Zero dispersion slope		≦0.091 ps/nm^2 · km	≦0.092 ps/nm^2 · km	≦0.092 ps/nm^2 · km
Typical value		0.086 ps/nm^2 · km	0.086 ps/nm^2 · km	0.04 ps/nm^2 · km
PMD				
Maximum Individual Fibre		≦0.1 ps/√km	≦0.1 ps/√km	≦0.1 ps/√km
Link Design Value(M=20,Q=0.01%)		≦0.06 ps/√km	≦0.06 ps/√km	≦0.06 ps/√km
Typical value		0.04 ps/√km	0.04 ps/√km	0.04 ps/√km
Cable cutoff wavelength λcc		≦1260 nm	≦1260 nm	≦1260 nm
Mode field diameter(MFD)	1310nm	8.7~9.5 um	8.4~9.2um	8.4~9.2 um
	1550nm	9.9~10.9 um	9.3~10.3 um	9.3~10.3 um
Effective group index of refraction(Neff)	1310nm	1.466	1.466	1.466
	1550nm	1.467	1.467	1.467
Point discontinuities	1310nm	≦0.05 dB	≦0.05 dB	≦0.05 dB
	1550nm	≦0.05 dB	≦0.05 dB	≦0.05 dB
Geometrical Characteristics				
Fiber Core Diameter		9 +/-1um	9 +/-1um	9 +/-1um
Cladding diameter		125.0±0.7 um	125.0±0.7 um	125.0±0.7 um
Cladding non-circularity		≦1.0 %	≦0.7 %	≦0.7 %
Coating diameter		245.0±7 um	245.0±5 um	245.0±5 um
Coating-cladding concentricity error		≦12.0 um	≦12.0 um	≦12.0 um
Coating non-circularity		≦6.0 %	≦6.0 %	≦6.0 %
Core-cladding concentricity error		≦0.6 um	≦0.5 um	≦0.5 um
Curl(radius)		≧4 m	≧4 m	≧4 m
Delivery length		2.1 to 50.4 km/reel	2.1 to 50.4 km/reel	2.1 to 50.4 km/reel

*Attenuation loss of barefiber

Fiber Core Specifications (Multimode)

Characteristics		62.5/125 (OM1)	50/125 (OM2)	OM3/OM4	OM5
Geometry Characteristics					
Core Diameter		62.5±2.5 um	50±2.5 um	50±2.5 um	50±2.5 um
Core Non-circularity		≦5.0 %	≦5.0 %	≦5.0 %	≦5.0 %
Cladding Diameter		125.0±1.0 um	125.0±1.0 um	125.0±1.0 um	125.050±1.0 um
Cladding Non-circularity		≦1.0 %	≦1.0 %	≦0.6 %	≦0.6 %
Coating Diameter		245±7 um	245±7 um	245±7 um	245±7 um
Coating/Cladding Concentricity Error		≦10.0 um	≦10.0 um	≦10.0 um	≦10.0 um
Coating Non-circularity		≦6.0 %	≦6.0 %	≦6.0 %	≦6.0 %
Core/Cladding Concentricity Error		≦1.5 um	≦1.5 um	≦1.0 um	≦1.0 um
Delivery Length		up to 17.6 km/reel	up to 17.6 km/reel	up to 8.8 km/reel	up to 8.8 km/ reel
Optical Characteristics *					
Attenuation	850nm	≦2.3 dB/km	≦2.3 dB/km	≦2.3dB/km	≦2.3 dB/km
	953nm	-	-	-	≦1.7 dB/km
	1300nm	≦0.55 dB/km	≦0.55 dB/km	≦0.55 dB/km	≦0.55 dB/km
Overfilled Modal Bandwidth	850nm	≧200 MHz · km	≧500 MHz · km	≧1500/≧3500 MHz · km	≧3500 MHz · km
	953nm	-	-	-	≧1850 MHz · km
	1300nm	≧500 MHz · km	≧500 MHz · km	≧500/≧500 MHz · km	≧500 MHz · km
Effective Modal Bandwidth	850nm	-	-	≧2000/≧4700 MHz · km	≧4700 MHz · km
	953nm	-	-	-	≧2470 MHz · km
10Gb/sWDM		-	-	-100/150 m	150 m
40Gb/sWDM		-	-	300/500 m	440 m
40GBASE-SR4 / 100GBASE SR10	850nm	-	-	1000/1100 m	200 m
10GBASE-SR	850nm	-	150 m	300/500 m	-
1000BASE-SR	850nm	-	750 m	1000/1100 m	-
DMD Specification		-	-	-	-
Numerical Aperture		0.275±0.015	0.200±0.015	0.200±0.015	0.200±0.015
Group Refractive index		1.496	1.482	1.482	1.482
		1.491	1.477	1.477	1.477
Zero Dispersion Wavelength, λ_0		1320-1365 nm	1295-1340 nm	1295-1340 nm	1297-1328 nm
Zero Dispersion Slope,S_0		-	-	-	≦4(-103)/(840λ√840)^4)
		-	-	-	ps/nm^2 · km
Zero Dispersion Slope,S0	1295nm≦λ_0≦1310nm	-	≦0.105 ps/nm^2 · km	≦0.105 ps/nm^2 · km	-
	1310nm≦λ_0≦1340nm	-	≦0.000375(1590-λ_0) ps/nm^2 · km	-	-
	1320nm≦λ_0≦1348nm	≦0.11 ps/nm^2 · km	-	≦0.000375(1590-λ_0)ps/nm^2 · km	-
	1348nm≦λ_0≦1365nm	≦0.001(1458-λ_0) ps/nm^2 · km	-	-	-

*Attenuation loss of barefiber

© LIGHTEM® Group All rights reserved. Specifications are subject to change without notice

Ordering Information

* Ordering Code Example



© LIGHTEM® Group All rights reserved. Specifications are subject to change without notice